

TECHNICAL DATA

Mylar®

850

■ Characteristics

Heatsealable Polyester film

■ Typical Applications

Packaging

■ Pretreatment

none

■ Technical Data

Item	Unit	850 Type	Test method
Thickness	μ m	20	JIS C2151
Tensile strength	MD	190	JIS C2318
	TD	200	
Tensile elongation	MD	100	JIS C2318
	TD	90	
Thermal Shrinkage (150 deg C × 30 mins.)	MD	1.3	JIS C2318
	TD	0.3	
Coefficient of friction	μ s	0.4	JIS C7175
	μ k	0.5	
Haze	%	4.5	JIS K7136

1.The information contained herein is believed to be reliable and correct.

2.Please refer to the MSDS for product safety data.

3.Information is presented without guarantee or warranty.