

TECHNICAL DATA

Teijin Teton Films CV

■ Characteristics

Thin film with superior handling property

■ Typical Applications

Thermal transfer ribbon, Capacitor

■ Pretreatment

none

■ Technical Data

Item		Unit	CV Type						Test method
Thickness		μ m	5	6	9	12	14	16	JIS C2151
Tensile strength	MD	MPa	250	250	250	250	250	250	JIS C2318
	TD		260	260	260	260	260	260	
Tensile elongation	MD	%	90	90	90	90	90	90	JIS C2318
	TD		80	80	80	80	80	80	
Thermal Shrinkage (150 deg C × 30 mins.)	MD	%	1.9	1.9	1.9	1.9	1.9	1.9	JIS C2318
	TD		0.9	0.9	0.9	0.9	0.9	0.9	
Coefficient of friction	μ s	-	0.5	0.5	0.5	0.5	0.5	0.5	JIS C7175
	μ k		0.5	0.5	0.5	0.5	0.5	0.5	

1.The information contained herein is believed to be reliable and correct.

2.Please refer to the MSDS for product safety data.

3.Information is presented without guarantee or warranty.