

TECHNICAL DATA

Teijin Teton Films HB

■ Characteristics

Very Clear Weatherable film containing UV absorbent

■ Typical Applications

Green House, solar film, explosion-proof film

■ Pretreatment

Adhesion Promotion, Slip

■ Technical Data

Item	Unit	HB Type		Test method
Thickness	μm	25	50	JIS C2151
Tensile strength	MD	240	240	JIS C2318
	TD	270	250	
Tensile elongation	MD	160	160	JIS C2318
	TD	120	120	
Thermal Shrinkage (150 deg C × 30 mins.)	MD	1.0	1.0	JIS C2318
	TD	0.9	0.9	
Coefficient of friction	μs	0.4	0.4	JIS C7175
	μk	0.3	0.3	
Haze	%	0.3	0.4	JIS K7136

Thermal Shrinkage: MD of 75, 100 μm is 100deg × 30 minute.

1.The information contained herein is believed to be reliable and correct.

2.Please refer to the MSDS for product safety data.

3.Information is presented without guarantee or warranty.