

## TECHNICAL DATA

### Teijin Teton Films SL

#### ■ Characteristics

Improved dimensional stability at high temperature  
(Base film : S Type)

#### ■ Typical Applications

FPC, MTS, substrate for various coatings

#### ■ Pretreatment

Adhesion Promotion

#### ■ Technical Data

Item		Unit	SL Type						Test method
Thickness		μm	38	50	75	100	125	188	JIS C2151
Tensile strength	MD	MPa	220	210	200	200	200	190	JIS C2318
	TD		260	250	240	240	240	200	
Tensile elongation	MD	%	180	190	190	190	190	200	JIS C2318
	TD		130	130	140	140	140	160	
Thermal Shrinkage (150 deg C × 30 mins.)	MD	%	0.4	0.4	0.4	0.4	0.4	0.4	JIS C2318
	TD		-0.1	-0.1	-0.1	-0.1	-0.1	-0.1	
Coefficient of friction	μs	-	0.3	0.3	0.3	0.3	0.3	0.3	JIS C7175
	μk		0.4	0.4	0.4	0.3	0.3	0.3	
Haze		%	3.0	4.0	5.0	7.0	8.0	12.0	JIS K7136

- 1.The information contained herein is believed to be reliable and correct.
- 2.Please refer to the MSDS for product safety data.
- 3.Information is presented without guarantee or warranty.