

TECHNICAL DATA

Teijin Teton Films

U4

■ Characteristics

Milky translucent film with superior light diffusion property

■ Typical Applications

Release liner, Stamping foil, Label overlay

■ Pretreatment

none

■ Technical Data

Item	Unit	U4 Type			Test method	
Thickness	μm	23	38	50	JIS C2151	
Tensile strength	MD	MPa	200	200	200	JIS C2318
	TD		210	210		
Tensile elongation	MD	%	90	110	110	JIS C2318
	TD		80	90		
Thermal Shrinkage (150 deg C \times 30 mins.)	MD	%	1.8	1.1	1.0	JIS C2318
	TD		0.3	0.3		
Coefficient of friction	μs	-	0.3	0.3	0.3	JIS C7175
	μk		0.3	0.3		
Haze	%	72	80	86	JIS K7136	

1.The information contained herein is believed to be reliable and correct.

2.Please refer to the MSDS for product safety data.

3.Information is presented without guarantee or warranty.